

IN THE CLAIMS.

1. (Currently Amended) A method of analysis of a printed circuit board comprising:
generating a pixelated image of the printed circuit board, said printed circuit board comprising
a laminate and a plurality of metal conductors; and
determining the presence of ~~an oxide on a metal~~ oxidized metal on a conductor from an
analysis of the image.
2. (Currently Amended) A method according to claim 1 wherein determination of the
presence of ~~an oxide~~ oxidized metal is made without determining whether the pixel is a laminate
pixel.
3. (Currently Amended) A method according to claim 1 wherein generating an image
comprises generating a pixelated image having brightness values for each pixel and wherein
determining the presence of ~~the of an oxide~~ oxidized metal comprises determining the presence
of the ~~oxide~~ oxidized metal responsive to the brightness values.
4. (Currently Amended) A method according to claim 1 wherein generating an image
comprises generating a plurality of images each at a different color and having brightness values
for each pixel in each image and wherein determining the presence of ~~an oxide~~ oxidized metal
includes making the determination based on an analysis of the pixel values in at least two of the
images.
5. (Original) A method according to claim 4 wherein the plurality of images comprises a
red, a green and a blue image.

6. (Currently Amended) A method according to claim 4 wherein determination of the presence of ~~an oxide~~ oxidized metal includes eliminating pixels from consideration based on a brightness value for a single color.

7. (Previously Presented) A method according to claim 6 wherein the single color is red and wherein pixels having a red brightness level below a given value are eliminated from consideration as being an oxide.

8. (Previously Presented) A method according to claim 6 wherein the single color is red and wherein pixels having a red value above a given value are eliminated from consideration as being an oxide.

9. (Previously Presented) A method according to claim 6 wherein determination of the presence of an oxide includes eliminating pixels from consideration based on a comparison between the brightness level of two colors.

10. (Original) A method according to claim 9 wherein the two colors are red and green and wherein the pixel is eliminated if its red brightness value compared to that of copper is less than its green brightness value compared to copper.

11. (Previously Presented) A method according to claim 9 wherein the two colors are red and blue and wherein the pixel is eliminated if its red brightness value compared to that of copper is less than its blue brightness value compared to copper.

12. (Currently Amended) A method according to claim 6 wherein determination of the presence of an ~~oxide~~ oxidized metal includes eliminating pixels from consideration based on an analysis of the brightness levels of three colors.

13. (Currently Amended) A method according to claim 6 wherein determination of the presence of an ~~oxide~~oxidized metal includes eliminating pixels from consideration based on a comparison between the brightness level of three colors with brightness levels for copper.

14. (Original) A method according to claim 13 wherein a pixel is eliminated from consideration as an oxide when its color brightness values have a Mahalanobis distance greater than a given value from the mean values of the brightness values for copper.

15. (Original) A method according to claim 14 wherein the given value for the Mahalanobis distance is between 4 and 8.

16. (Original) A method according to claim 14 wherein the given value for the Mahalanobis distance is about 6.

17. (Currently Amended) A method according to claim 2 wherein the determination of the presence of an ~~oxide~~oxidized metal is made based on a relationship between the brightness values of the image and brightness values characteristic of copper.

18. (Currently Amended) A method according to claim 4 and comprising:
determining a color gamut characteristic of the ~~oxide~~oxidized metal; and
comparing the color values of a pixel to the determined gamut of values to determine if the pixel is an ~~oxide~~oxidized metal.

Claims 19 - 22. (Canceled)

23. (Currently Amended) A method according to claim 12 and comprising:
determining a color gamut characteristic of an ~~oxide~~oxidized metal; and

AMENDMENT UNDER 37 C.F.R. § 1.114(c)
US APPLICATION NO. 09/762,945
ATTORNEY DOCKET NO. Q80251

comparing the color values of a pixel to the determined gamut to determine if the pixel is an
| ~~oxide~~oxidized metal.